LABPOX® 40 UV SUPER OPAQUE WHITE

100% Solids, High-Performance Epoxy Providing a Superior UV Resistance

Technical Data Sheet

DESCRIPTION

The LABPOX® 40 UV SUPER OPAQUE WHITE is a 100% solids, two-component (2A:1B), zero VOC specialty epoxy designed for concrete floor coatings with optimal UV resistance. Available in white, the product exhibits high opacity and superior resistance to UV irradiation (color retention over time), making it best suited for residential and commercial applications. Ideal for bright white floors or as base coat for metallic systems. The LABPOX® 40 UV SUPER OPAQUE WHITE can be used as a base coat. LABPOX® 40 UV SUPER OPAQUE WHITE must be protected with an AQUALAB® PUR, LABFAST®, LABSHIELD® ECO or LABFENDER® topcoat product. The LABPOX® 40 UV SUPER OPAQUE WHITE protective topcoat product is based on high-performance cycloaliphatic polyamine technology, displaying outstanding properties and delivering a superior aesthetic finish.

USES

The LABPOX® 40 UV SUPER OPAQUE WHITE provides excellent results for the following applications:

+ Airplane hangars
+ Commercial, residential, and industrial uses
+ Base for metallic systems
+ Commercial centers
+ Office buildings
+ Retail stores
+ Warehouses
+ Garages
+ Growing facilities
+ Public facilities including hospitals and schools
+ Pharmaceutical companies

ADVANTAGES

+ Three time the opacity of regular white epoxy
+ Offering one of the best UV resistances in its category
+ Environment friendly (100% solids, no solvent and zero VOC content)
+ Potential for LEED eligibility
+ Virtually odor-free
+ Easy application with long pot life and working time (60 min)
+ Ideal as a base for metallic epoxy systems
+ Good elongation and excellent abrasion resistance
+ High resistance to amine blush and contamination (fisheyes)
+ Excellent defoaming even at thicker levels
+ Impermeability / low moisture sensitivity
+ High density of the product prevents dirt penetration resulting in low maintenance post application

PRODUCT DATA

Mix Ratio	2A:1B	
Packaging	3 Gal kit (3 x 3.78 L)	
Color	Clear, Super Opaque White	
Solids Coverage / GAL	Mils	Sq. Ft.
	8	200
	10	160
	12	133
	16	100
Shelf Life	One year, in original unopened factory pails under normal storage conditions	
Pot Life	50 min	
Application temperature	Min 16°C / 61°F, Max 30°C / 86°F	
Cure Time	**22°C / 72°F and 50% Rel. Hum.**	
Working time	55 min	
Tack Free	9 h	
Recoat	9 - 24 h	
Dry Through	13 h	
Foot Traffic	24 h	
Light Traffic	48 h	
Full Cure	1 week	

TECHNICAL PROPERTIES

Hardness ASTM D2240	80 Shore D at maturity
Abrasion Resistance ASTM D4060 (Taber Abraser, Wheel CS 17/1000 g (2.2 lbs) / 1000 cycles)	65 mg loss
DRY Coefficient of Friction (Smooth coating) ASTM E303	0.9
Pull Off Test ASTM D7234	>3 Mpa
Elongation at break ASTM D638	91%
Tensile Strenght ASTM D638	4250 psi
Compresive Strenght ASTM D695	8000 psi (90 Mpa)
Solids Content by Volume	100%
Viscosity (A&B)	800 +/-100 cps
VOC Content	0 g/l

2026 © Labsurface. All rights reserved.

SURFACE PREPARATION

Concrete should be clean, dry and free of grease, oil, paint, curing agents or any contaminants that may inhibit proper adhesion. Concrete should be cured at least 28 days before applying the coating system. If the concrete slab has been installed within 28 days, the LABPOX® MVB FAST moisture mitigation system can be considered system (refer to the LABPOX® MVB FAST technical data sheet for application details).

Proper testing procedures should be practiced with regards to moisture vapor transmission. Use a Tramex® CME / CMExpert to measure the moisture content of the concrete slab. Moisture content must be below 4% before applying the product. It is necessary to take several measurements at various places on the slab. If the reading is higher than 4%, steps will be required to neutralize the soil moisture. The first thing to do is to make sure that the floor is completely dry before application. Floors with higher results can receive the LABPOX® MVB FAST moisture mitigation.

Surface must be shot blasted or prepared with an equivalent mechanical means in line with CSP-2 or more depending on the application. Ensure the surface is free of contaminants, and the pores are open to allow the product to penetrate.

If the product is applied over an existing LABPOX® flooring system that has been cured for a period longer than 24 hours, it should be sanded with a proper floor machine. A mechanical bond to a sanded surface is required and the pores of the existing coating must be opened for better adhesion. Vacuum dust and properly wipe the surface with alcohol or solvent prior applying the LABPOX® 40 UV SUPER OPAQUE WHITE. The alcohol or solvent must be completely evaporated before applying the product. This preparation is necessary to ensure proper adhesion. Conduct adhesion tests if there is a doubt about surface preparation.

When installing a broadcast decorative system, after appropriate hardness has been reached, the base coat in which the aggregates are broadcasted should be carefully scraped and swept and then thoroughly vacuum cleaned to remove any remaining residues prior applying the topcoat. Contact us for more details on how to use the product with broadcast systems.

MIXING

Before final mixing, pre-mix part A at low speed using a Jiffy® or an Exomixer® mixer blade. Mixing should be done until the color is uniform.

Use the same batch number when more than one kit is required. In the event that different batch numbers have to be use for a same job, we recommend pre-mixing all part A's individually, then mix together part A's from the different batch numbers for two minutes until homogenous color.

Then, using a Jiffy® or an Exomixer® mixer blade, mix two parts of A and one part of B together at low speed in a separate container. The mixing container must be clean and free of any outside particle. Mix thoroughly for a minimum of three minutes, until a completely homogeneous mixture is obtained. Use a low-speed drill (300-450 rpm) to minimize the air entrapment. It is recommended to activate the mixer in the reverse mode after the first 90 seconds for the liquid to mix from the bottom of the mixing can to the top. Make sure to scrape sides and bottom of mixing container so no unmixed material remains. Mix only the necessary quantity to be used according to the specified pot life / working time. Once the product is properly mixed, it needs to be immediately poured on the floor. Leaving mixed material for too long in a mixing pail will create an exothermic reaction and the product will no longer be usable.

APPLICATION

The LABPOX® 40 UV SUPER OPAQUE WHITE is to be uses as a basecoat layer only. The product can also be used as a base layer for metallic floor systems. The LABPOX® 40 UV SUPER OPAQUE WHITE can not be used as a primer. LABPOX® 40 UV SUPER OPAQUE WHITE should never be left exposed. It must be protected with a protective topcoat such as AQUALAB® PUR, LABFAST®, LABSHIELD® ECO or LABFENDER® product. In addition to the superior chemical resistance and cleanability, the matte version of the AQUALAB® PUR possesses a unique characteristic which is to make the scratches less apparent. The AQUALAB® PUR, LABFAST®, LABSHIELD® ECO or LABFENDER® products also provide additional UV protection that will significantly slow the yellowing of the epoxy..

Apply only when air and slab temperature is between 16°C / 61°F - 30°C / 86°F and the relative humidity of less than 85%. If a heated floor is installed, ensure that the system is turned off 2-4 hours (depending on type of radiant floor) before application and for the full duration of the cure. The product has been designed to adhere to concrete surfaces.

For standard systems, one coat of 15 mils should be enough to provide complete opacity. Do not exceed 20 mils. Porous or soft concrete will require more base coat resin to achieve full saturation.

It is crucial to prevent sweat or water droplets from coming into contact with the product while blending or installing the product. This precaution is necessary to avoid the formation of circles and/or fisheyes. Additionally, wall-mounted Air Wick type devices and aerosols should be avoided during both the installation and drying processes, as they can also cause circles or fisheyes.

2026 © Labsurface. All rights reserved.

We recommend the LABTEC Vinyl Chips when installing a flake system. Proper testing should be conducted prior application.

RECOAT

Do not recoat without sanding if last coating of the product has been applied for more than 24 hours. The floor surface should be sanded/abraded until a uniform dullness is achieved. There should be no gloss on the prior coating after vacuuming and before applying the next coat.

Available Colors

Super Opaque White

LIMITATIONS

Requires a dry substrate. Moisture content of the substrate must be measured with a Tramex® CME / CMExpert and must be below 4% before applying the product. This product should not be applied to concrete substrates that show high levels of moisture/humidity unless a moisture a LABPOX® MVB FAST moisture mitigation system is used. LABPOX® 40 UV SUPER OPAQUE WHITE should never been left exposed. It is mandatory to use a protective topcoat such as AQUALAB® PUR, LABFAST®, LABSHIELD® ECO or LABFENDER® over it. Although this product may be applied in a wide range of thickness, limitations may apply when taking into consideration curing time. Everything else being equal, thicker is the film, quicker is the curing time. Drying time will be faster in a hot environment. Conversely, the drying time will be longer in a cold environment and the appearance of the surface may be affected. Leaving mixed material for too long in a mixing pail will create an exothermic reaction and the product will no longer be usable. Do not clean the finished surface during the week following installation. Keep the product stored at room temperature to ensure consistent results. Not suited for exterior applications. Although Labsurface makes reasonable efforts to control the quality of the finished product and its components, ASTM results may vary depending on the quality of the inputs delivered to Labsurface.

To ensure UV resistance performance of the product, do not use a LABPOX® 30's part A or B or other LABPOX® products with the LABPOX® 40 UV SUPER OPAQUE WHITE. UV resistance may decrease depending on storage conditions (including exposure to heat, humidity, and light) and the duration of storage before application. Failure to comply with the recommended storage conditions in this technical data sheet or on the product label may result in actual performance lower than advertised.

In the event that dew point conditions lead to condensation persisting above the concrete surface, and for which the grinding process fails to eliminate this condensation, it is crucial to thoroughly dry the surface before installation. Neglecting this step may result in adhesion issue.

While resinous coatings provide excellent chemical and mechanical resistance, they are not immune to osmotic, alkali-silica reaction (ASR) or hydrostatic pressure. Moisture in the substrate may adversely affect coating performance such as blistering, delamination, or other coating failures.

The usage of direct-fired, unvented and certain other heat sources are not recommended as they emit byproducts that may negatively impact the curing process of the resin and lead to defects such as whitening, loss of adhesion, or other surface imperfections.

Labsurface stands behind the quality of its products. However, Labsurface cannot guarantee results since Labsurface has no control over surface preparation, operating conditions, and application procedures. Clients are solely responsible to test Labsurface's products to determine if they perform as expected.

To meet our strict requirements, we are continuously testing our coatings and on occasion, formulations may be modified to improve certain properties within each coating. Information and data included in this reference document may not be up to date as of the date of reference. Contact Labsurface for further information regarding the limitations of this product.

This product is not immune to transfers of plasticizers contained in rubber, including car tires. Although the transfer of plasticizers phenomenon is very rare, under specific circumstances combining high tire temperature with i) high levels of plasticizers, and/or (ii) certain plasticizer types and/or (iii) certain tire types, it is possible for plasticizers to transfer from the tire rubber to the floor coating. This phenomenon is irreversible and can cause staining of the coated area. Tires should therefore cool down prior to the parking of the vehicle in the coated area.

Pressure washing and power washing (power washing involves water heating while pressure washing uses cold water) must be used with caution. Extreme pressure could damage the coating. Using hot water could also cause irreversible damage. When used to clean polymer coatings, water temperature must not exceed 49°C / 120°F and should be ideally between 32°C and 43°C / 90°F and 110°F.

Exposure to certain chemicals may cause reactions similar to those experienced with allergies. Chemicals that may cause sensitivity include synthetic and natural substances found in the Part A or the Part B of flooring or casting products. Once cross

2026 © Labsurface. All rights reserved.

linked and completely cured, those substances are inert and therefore should not result in allergic reactions. Raw materials used by Labsurface do not differ significantly from comparable products manufactured by our competitors.

Refer to the most recent Material Safety Data Sheet prior using this product.

LABSURFACE

2250, Louis-Blériot, Mascouche, (QC) CANADA J7K 3C1
Phone: 450 966-9000 / Fax : 450 621-3135
Labsurface.com

LABSURFACE GENERAL INDUSTRY WARRANTY

Labsurface products are researched, developed and manufactured to be free of defects in material and workmanship in meeting the properties specified on each of Labsurface's product or individual system guide Technical Data Sheets. Buyers, Owners, Specifiers, Users and Installers of Labsurface products & systems are solely responsible for determining the suitability of the products or systems for specific product applications. Labsurface makes no Warranty or Guarantee, expressed or implied, including warranties of fitness, design compatibility or merchantability, for any particular use and specifically disclaims implied warranties of merchantability and fitness for a particular purpose. Labsurface shall not be liable, regardless of the nature of the claim, and regardless of the person or entity making the claim, for special or incidental or consequential damages. The User's, Installer's, Specifier's, Owner's or Buyer's sole remedy will not exceed the purchase price or replacement cost of the Labsurface product. Replacement cost is the product cost only; it does not include labor costs.

Labsurface's Warranty is voided, and Labsurface assumes no liability of any nature, if Labsurface's products or systems are adjusted in the field or if the Buyer, Installer, Specifier, Owner or User does not utilize only Labsurface specified Labsurface products or components. If a Labsurface product or system is proven defective within one (1) year of its installation, Labsurface may, at its sole discretion, either replace the material or issue a credit to the customer's account equal to the original purchase price paid for that material, provided that the material proven defective was installed within its shelf life. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. Potential claims regarding product quality must be received in writing by Labsurface within 30 days of the discovery of such potential defect.

LABSURFACE SHALL NOT BE RESPONSIBLE FOR THE USE OF ITS PRODUCTS IN A MANNER THAT INFRINGES ON ANY PERSON'S INTELLECTUAL PROPERTY RIGHTS.

THIS WARRANTY IS THE ONLY WARRANTY OFFERED BY LABSURFACE. NO OTHER WARRANTIES, OR CHANGES TO THIS WARRANTY, ARE AUTHORIZED AND EFFECTIVE UNLESS IN WRITING, SIGNED BY AN OFFICER OF LABSURFACE.

2026 © Labsurface. All rights reserved.